Qingdao Tongli Packaging Products Co., Ltd Add: #510, No.1 Building, Image Shidai Center, Zhengyang Road,Qingdao, Shandong, China P.C.:266109 Tel: 0086-532-89082296 Fax: 0086-532-66721158

PRODUCT DESCRIPTION

	P	RODUCT PHOTO	ITEMS	DETAILS					
			PRODUCT-ID	TL-14					
			PRODUCT NAME	3L aluminum foil bag-in-box pouch with butterfly valve and handle for apple juice					
	Line -		TYPE	Bag-in-box					
	T.V.	100%	APPLICATION	Juice					
	2.1	Succo di	VOLUME	3L					
		mala	DIMENSION	W250 X H360+ BG140mm					
		Duce Kinée	FOIL STRUCTURE	PET12/AL7/PA15//LDPE160					
			THICKNESS	200 microns					
			CUSTOM	# Custom print # Butterfly Valve # Small Plastic Handle # Rounded Corners					
			VIDEO	https://www.youtube.com/watch?v=vMgOMvYa p3A					
EXPLA	EXPLAINATION ON FOIL STRUCTURE								
PA15: Biaxially orientated polyamide film, also call nylon film 15 microns LDPE: Low density polyethylene film human food grade There will be print inks and adhesive bonding layers which ranges from 2 to 3 gsm with thickness about 2 microns, so the final actual thickness of this foil laminate should be decided upon these factors.									
-	GOOD GRADE								
		nd adhesive used in our products are humar vww.valuepackaging.cn/human-food-grade/		ect to SGS test.					
SOME TEST FOR REFERENCE									
Serial	TEST	EXPLAIN		POST LINK					
1									
2									
3									
4									
5									

TECHNICAL DATA SHEET

NO.	ITEM		STANDARDS	UNIT	TYPICAL VALUE	VIDEO LINK		
1	Dimension	Height	INTERNAL	%	±1%			
		Width	INTERNAL	%	±1%			
		Gusset	INTERNAL	%	±5%			
		Seal Width	INTERNAL	%	±5%			
		Thickness	INTERNAL	%				
2	Print Appearance		INTERNAL					
3	Yield			grams/m2	210			
4	Tensile Strength	MD	ASTM-D-882	Мра	112.5			
		TD	ASTM-D-882	Мра	122.3			
F	Elongation	MD	- ASTM-D638	% @23 ℃	42.5			
5		TD		% @23 ℃	54.6			
6	COF	Outer		@23 °C	0.25			
		Inner		@23 °C	0.300000012			
7	Solvents Left		ASTM F1884	mg/m2	5-6			
8	Sealing Strength		ASTM F1884	mg/m2	45~50			
9	Sealing Conditions		0Celsius for 0 Seconds		onds			
10	Bond Strength		ASTM F 904	N/15mm	5-6			
11	Impact Strength				2.5			
12	Pressure Resistance		Q/3700SDXS	kg	80			
13	Drop Test Ability		Q/3700SDXS	cm	160			
14	4 Water Vapor Transimission Rate		ASTM E 96	g/m2/24hr	0.01			
15	Oxygen Transmission Rate		ASTM D 372-99	cc/m2/24hr	0.01			
This technical data sheet is intended to describe the products we are able to provide for our customers, and actual parameters should be subject to								

This technical data sheet is intended to describe the products we are able to provide for our customers, and actual parameters should be subject to the final test report provided by the manufacturer. If you have any questions regarding the test items, just reach us for further assistance.

China Manufacturer:

Add: No. 1010 Image Center, Zhengyang Road, Qingdao, China P.C:266100 Tel: 0086-532-89082296 Fax: 0086-532-66721158

 Web: www.valuepackaging.cn
 Email: office@valuepackaging.cn

 Take Around Our Factory
 https://www.youtube.com/watch?v=Dxo85MAECtw